

YI-LAI MARKETING SDN BHD (459342-W)

(Wholly Owned Subsidiaries of YB Ventures Berhad)

Office & Showroom In Malaysia:

Selangor

No. 8, Jalan 51A/241, Seksyen 51A, 46100 Petaling Jaya, Selangor
+603-7875 4388

Johor

No. 15 & 16, Jalan Tropika 1, Taman Tropika, 81000 Kulai, Johor
+607-663 7523

Melaka

No. 65, Jalan Suria 1, Taman Malim Jaya, 75250 Melaka
+606-336 7128

Penang

97-1-16, The Palazzia, Jalan Bukit Gambir, 11700 Gelugor, Pulau Pinang

Perak

No. 46A, Jalan Bendahara, 31650 Ipoh, Perak
+605-241 3729

YI-LAI TRADING PTE LTD (198204735-E)

Marketing Office In Singapore:

2 Sims Close #06-06 Gemini@Sims Singapore 387298
+65-6842 0163

AuraStone
H O M O G E N E O U S | R O U G H





MODEL: YLH66AU01C

AuraStone

 R11 anti slip




YLH63AU00C
300x600mm
Charcoal



YLH66AU00C
600x600mm
Charcoal




YLH63AU01C
300x600mm
White



YLH66AU01C
600x600mm
White



YLH63AU02C
300x600mm
Beige



YLH66AU02C
600x600mm
Beige




YLH63AU03C
300x600mm
Brown




YLH66AU03C
600x600mm
Brown



YLH63AU04DC
300x600mm
Dark grey



YLH66AU04DC
600x600mm
Dark grey



YLH63AU04LC
300x600mm
Light grey



YLH66AU04LC
600x600mm
Light grey

APPLICATION:



Wall



Floor



Indoors



Outdoors



Residential



Commercial



Wet Area



Dry Area



300x600mm Faces: 3 face

Tile Properties: Homogeneous | Bla | V2
Physical Appearance: Rough | Rectified



600x600mm Faces: 3 face


Tile Properties: Homogeneous | Bla | V2
Physical Appearance: Rough | Rectified

TECHNICAL SPECIFICATION FOR ALPHA HOMOGENEOUS TILE			
Symbol	Test	Specification	
		MS ISO 13006: 2020	YLI
	Water Absorption(%)	E≤0.5%	E≤0.1%
	Dimension: Length & Width (for non-rectified tiles)	±0.60% (max±2.0mm)	±0.50% (max±2.0mm)
	Dimension: Length & Width (for rectified tiles)	±0.30% (max±1.0mm)	±0.25% (max±1.0mm)
	Thickness	±5.0% (max±0.5mm)	±4.0% (max±0.5mm)
	Straightness Of Side (mm) for non-rectified tiles	±0.50% (max±1.5mm)	±0.50% (max±1.5mm)
	Straightness Of Side (mm) for rectified tiles	±0.30% (max±0.8mm)	±0.30% (max±0.8mm)
	Rectangularity (mm) for non-rectified tiles	±0.50% (max±2.0mm)	±0.50% (max±2.0mm)
	Rectangularity (mm) for rectified tiles	±0.30% (max±1.5mm)	±0.30% (max±1.5mm)
	a) Centre Curvature for non-rectified tiles	±0.50% (max±2.0mm)	±0.50% (max±2.0mm)
	a) Centre Curvature for rectified tiles	±0.40% (max±1.8mm)	±0.40% (max±1.8mm)
	b) Edge Curvature for non-rectified tiles	±0.50% (max±2.0mm)	±0.50% (max±2.0mm)
	b) Edge Curvature for rectified tiles	±0.50% (max±2.0mm)	±0.50% (max±2.0mm)
	c) Edge Curvature for non-rectified tiles	±0.40% (max±1.8mm)	±0.40% (max±1.8mm)
	c) Edge Curvature for rectified tiles	±0.50% (max±2.0mm)	±0.50% (max±2.0mm)
	Surface Quality*	±0.40% (max±1.8mm)	±0.40% (max±1.8mm)
	Modulus Of Rupture	Min 35 N/mm²	Min 35 N/mm²
	Scratch (Moh's Hardness Scale)	Min 6	Comply
	Abrasion Resistance (PEI)	Class I ~ IV	Comply
	Chemical Resistance To		
	a) Acid	GLA ~ GLC	Comply
	b) Alkaline	GLA ~ GLC	Comply
	Chemical Resistance To Stain	Min Class 3	Min Class 3
	Crazing Test	No Crazing	No Crazing (3 times)

* Free from visible defect


ALPHA PACKAGING SPECIFICATION										
DIMENSION	CARTON			PALLET			CONTAINER			
	Pieces	Weight(kg)	Sq.Meter	Cartons	Weight(kg)	Sq.Meter	Cartons	Pallets	Sq.Meter	Gross Weight(kg)
600x600mm	4	32.0	1.44	40	1305	57.60	640	17	979.20	20880
300x600mm	8	29.3	1.44	40	1197	57.60	720	18	1036.80	21546

Remarks:
The "kg/pallet" is included 25kg pallet weight | Bla=<0.1% water absorption | B1b=>0.5 to <3% water absorption



V1

UNIFORM
SHADE & TONE




V2

SLIGHT
VARIATION



V3

MEDIUM
VARIATION



V4

STRONG
VARIATION