

**YI-LAI MARKETING SDN BHD (459342-W)**

*(Wholly Owned Subsidiaries of YB Ventures Berhad)*

**Office & Showroom In Malaysia:**

**Selangor**  
No. 8, Jalan 51A/241, Seksyen 51A, 46100 Petaling Jaya, Selangor  
+603-7875 4388

**Johor**  
No. 15 & 16, Jalan Tropika 1, Taman Tropika, 81000 Kulai, Johor  
+607-663 7523

**Melaka**  
No. 65, Jalan Suria 1, Taman Malim Jaya, 75250 Melaka  
+606-336 7128

**Penang**  
97-1-16, The Palazzia, Jalan Bukit Gambir, 11700 Gelugor, Pulau Pinang

**Perak**  
No. 46A, Jalan Bendahara, 31650 Ipoh, Perak  
+605-241 3729

**YI-LAI TRADING PTE LTD (198204735-E)**


**Marketing Office In Singapore:**  
2 Sims Close #06-06 Gemini@Sims Singapore 387298  
+65-6842 0163

ErmeloSand  
P O R C E L A I N | M A T T E





# ErmeloSand



**YLH63EM00C**  
300x600mm      Graphite



**YLH63EM01C**  
300x600mm      Cool Grey



**YLH63EM02C**  
300x600mm      Beige



**YLH63EM04C**  
300x600mm      Warm Grey

APPLICATION:



Wall



Floor



Indoors



Outdoors



Residential




Commercial



Wet Area



Dry Area



300x600mm Faces: 8 face


Tile Properties: Porcelain | B1b | V3  
Physical Appearance: Matte | Rectified

| TECHNICAL SPECIFICATION FOR ALPHA PORCELAIN RECTIFIED TILE                            |                                                     |                    |                      |
|---------------------------------------------------------------------------------------|-----------------------------------------------------|--------------------|----------------------|
| Symbol                                                                                | Test                                                | Specification      |                      |
|                                                                                       |                                                     | MS ISO 13006: 2020 | YLI                  |
|    | Water Absorption(%)                                 | E≤0.5%             | E≤0.3%               |
|    | Dimension: Length & Width (for non-rectified tiles) | ±0.60% (max±2.0mm) | ±0.50% (max±2.0mm)   |
|                                                                                       | Dimension: Length & Width (for rectified tiles)     | ±0.30% (max±1.0mm) | ±0.25% (max±1.0mm)   |
|    | Thickness                                           | ±5.0% (max±0.5mm)  | ±4.0% (max±0.5mm)    |
|    | Straightness Of Side (mm) for non-rectified tiles   | ±0.50% (max±1.5mm) | ±0.50% (max±1.5mm)   |
|                                                                                       | Straightness Of Side (mm) for rectified tiles       | ±0.30% (max±0.8mm) | ±0.30% (max±0.8mm)   |
|    | Rectangularity (mm) for non-rectified tiles         | ±0.50% (max±2.0mm) | ±0.50% (max±2.0mm)   |
|                                                                                       | Rectangularity (mm) for rectified tiles             | ±0.30% (max±1.5mm) | ±0.30% (max±1.5mm)   |
|    | a) Centre Curvature for non-rectified tiles         | ±0.50% (max±2.0mm) | ±0.50% (max±2.0mm)   |
|                                                                                       | a) Centre Curvature for rectified tiles             | ±0.40% (max±1.8mm) | ±0.40% (max±1.8mm)   |
|                                                                                       | b) Edge Curvature for non-rectified tiles           | ±0.50% (max±2.0mm) | ±0.50% (max±2.0mm)   |
|                                                                                       | b) Edge Curvature for rectified tiles               | ±0.50% (max±2.0mm) | ±0.50% (max±2.0mm)   |
|                                                                                       | c) Edge Curvature for non-rectified tiles           | ±0.40% (max±1.8mm) | ±0.40% (max±1.8mm)   |
|                                                                                       | c) Edge Curvature for rectified tiles               | ±0.50% (max±2.0mm) | ±0.50% (max±2.0mm)   |
|    | Surface Quality*                                    | ±0.40% (max±1.8mm) | ±0.40% (max±1.8mm)   |
|    | Modulus Of Rupture                                  | Min 35 N/mm²       | Min 35 N/mm²         |
|    | Scratch (Moh's Hardness Scale)                      | Min 6              | Comply               |
|   | Abrasion Resistance (PEI)                           | Class I ~ IV       | Comply               |
|  | Chemical Resistance To                              |                    |                      |
|                                                                                       | a) Acid                                             | GLA ~ GLC          | Comply               |
|                                                                                       | b) Alkaline                                         | GLA ~ GLC          | Comply               |
|  | Chemical Resistance To Stain                        | Min Class 3        | Min Class 3          |
|  | Crazing Test                                        | No Crazing         | No Crazing (3 times) |

\* Free from visible defect


| ALPHA PACKAGING SPECIFICATION |        |            |          |         |            |          |           |         |          |                  |
|-------------------------------|--------|------------|----------|---------|------------|----------|-----------|---------|----------|------------------|
| DIMENSION                     | CARTON |            |          | PALLET  |            |          | CONTAINER |         |          |                  |
|                               | Pieces | Weight(kg) | Sq.Meter | Cartons | Weight(kg) | Sq.Meter | Cartons   | Pallets | Sq.Meter | Gross Weight(kg) |
| 300x600mm                     | 8      | 24.7       | 1.44     | 60      | 1507       | 86.40    | 720       | 12      | 1036.80  | 18084            |

Remarks:  
The "kg/pallet" is included 25kg pallet weight | B1a=<0.5% water absorption | B1b=>0.5 to <3% water absorption




V1

UNIFORM  
SHADE & TONE



V2

SLIGHT  
VARIATION



V3

MEDIUM  
VARIATION



V4

STRONG  
VARIATION